

TECHNICAL SPECIFICATIONS OF WHITE PUTTY:

Appearance	white powder
Compressive strength @ 28 days	38Kg/Cm2
Putty water ratio	3:1
Setting time- initial	310 minutes
Final	405 minutes
Pot life	2 to 3 hrs. (Temp. 30-degree, RH 65%)
Dry for recoat	6 to 8 hrs (Temp.30 degree, RH65%)
Shelf life	1 year
Tensile adhesion test – 28 days	3.73 Kg/Cm2
Water retentivity test (%)	98.94%
Coverage	10 – 14 Sq. Feet/Kg.