

Specification of Eucalyptus Wood Chips

SI NO	<u>SPECIFICATION</u>	PARAMETERS
1	Size distribution (TAPPI UM 21 by mechanical screen test)	
a)	Over 28.6 mm	4.5%
b)	22.2 mm - 28.6 mm	17.0%
c)	9.5 mm - 22.2 mm	65%
d)	4.8 mm -9.5 mm	11.1%
e)	Under 4.8 mm	1.9%
f)	4.8 mm -28.6 mm	90.0%
2	Bark	0.60%
3	Rotten Wood	0.001%
4	Average Moisture content	45.46%
	The above parameters represents our finding at the time and place of inspection of one of the last shipments and can vary slightly vary.	