

Foundry Coke

Parameters	Foundry Coke (90-150)
Size MM	90-150
Ash % Max	12.75%
V.M.% Max	1.50%
F.C. % Min	86.00%
P % Max	0.05%
S % Max	0.60%
Moisture % Max	5%
CSR	65
CRI	24

Coke Breeze

Parameters	Coke breeze
Size MM	-10
Ash % Max	26%
V.M. % Max	7.0%
F.C. % Min	67.0%
P % Max	0.05%
S % Max	0.60%
Moisture % Max	10%

Parameters	Foundry Coke (90-150)
Size MM	90-150
Ash % Max	12.75%
V.M.% Max	1.50%
F.C. % Min	86.00%
P % Max	0.05%
S % Max	0.60%
Moisture % Max	5%
CSR	65
CRI	24